
Polygood[®] Material Data Sheet









Content

- 01 About Polygood®
- 01 Product Composition
- 02 Certifications
- 03 Specifications
- 04 Pattern Groups
- 05 Group I. Light patterns
- 08 Group II. Dark patterns
- 10 Group III. Terrazzo patterns
- 12 Group IV. Grey & Emerald
- 14 Group V. Marbellous
- 16 Group VI. Translucent patterns
- 19 Group VII. Salt Dune

⁰³ Product

6

About Polygood®

Polygood[®] stands as a remarkable achievement in sustainable surface materials. It's a Cradle to Cradle Certified[®] Bronze material, reflecting our unwavering commitment to environmental responsibility. Made entirely from 100% recycled and recyclable plastic, Polygood[®] panels are the only large-scale sustainable product of their kind. Each panel's composition consists of a single type of recycled



plastic, ensuring both simple recycling and robust, long-lasting quality.

The patterns derive from an array of postconsumer and post-industrial plastic waste sources, including items like refrigerators, singleuse cutlery, household appliances, and manufacturing components.



Product Composition

100% recycled polystyrene

The Good Plastic Company has chosen recycled plastic as its sole material due to the company's commitment to reducing waste and contributing to the circular economy. This recycled plastic is sourced from EuCertPlast-certified suppliers specializing in recycling polystyrene derived from electronic and Waste from Electrical and Electronic

Key





Scratch resistant

UV resistant

Waterproof

Equipment (WEEE), as well as post-consumer and post-industrial waste sources. Recycled polystyrene (rPS), which forms the entire composition of Polygood[®] panels, was selected due to its lower energy demand compared to other polymers during the production process, thereby reducing environmental impact.

4

Certifications⁰⁴

Polygood[®] is the first material of its kind to achieve many certifications that validate the company's leadership in sustainable materials.



The Cradle to Cradle[®] Bronze product propels Polygood to the forefront of the sustainable surface materials segment, offering architects, designers, and brands a trusted solution backed by rigorous analysis, audit, and testing. Polygood[®] is the first material of its kind to achieve this certification, solidifying The Good Plastic Company's position as an industry leader in sustainable materials and marking a significant milestone for the company.



Polygood[®] has been granted a verified Environmental Product Declaration (EPD). This accomplishment underscores our unwavering commitment to sustainability. An EPD includes the assessment of a product's environmental characteristics throughout its entire lifecycle, covering the entire value chain: from material extraction to production, product use, and end-of-life disposal.



A VOC A+ rating indicates that the surface material emits very low levels of VOCs into the indoor environment.

Polygood[®] aligns with BREEAM standards for construction materials, making it a low-VOC emitting material. We have conducted extensive tests to ensure that Polygood[®] doesn't emit any harmful substances.

⁰⁵ Specifications

Note: all imperial measurements provided in parentheses in this document are approximate and provided for convenience only. Please only place reliance on metric measurements.

Thickness tolerance:

+/- 0.5 mm (+/- 0.02")

Dimensions:

2800 x 1400 mm (110" x 55")

Finishes:

12 mm (1⁄2") 19 mm (3⁄4") Standard: semi-matte, single-faced Available upon request: semi-gloss, high-gloss, or double-faced Coatings: scratch-resistant, fire-resistant

Panel weight:

50-78 kg (110-172 lbs)

Thickness gauges:





Pattern Groups ⁰⁶



I — Light



II — Dark



III — Terrazzo



IV — Grey & Emerald



V — Marbellous





VI — Translucent

VII — Salt Dune

⁰⁷ Group I – Light



Madrid Content City by Dear Design, Revolución Limo Spain





Table collection by Hello Again Design Switzerland & Germany



Bathroom designs Netherlands



Installation for Paris Design Week 2023 France





Group I – Light ⁰⁸



 $\bigcirc \underline{\mathscr{A}}$

0 ./

0 1

VICTORIOUS #PS1507 Refrigerators And CD Cases



SEA FOAM GREY #PS2404 Refrigerators and spools, CNC shavings



WHITE TERRAZZO O #PS2107 Refrigerators, single-use plastic cutlery



WHITE LOLLIPOP #PS1601

Refrigerators and single-use plastic cutlery




TIMELESS DUO #PS1201 Consumer electronics, spools and refrigerators

VINTAGE PEARL #PS1101 Refrigerators 0 <u>.//</u>

MILKY WAY #PS1104 Refrigerators

 $\bigcirc \underline{\mathscr{A}}$





⁰⁹ Group I – Light



Test name	ISO	Indicator
Tensile modulus	ISO 527-2:2012 (method A)	1878 MPa
Tensile strength	ISO 527-2:2012 (method A)	22 MPa
Modulus of elasticity	ISO 178:2010 (method B)	1927 N/mm ²
Flexural strength	ISO 178:2010 (method B)	49.64 N/mm ²
Izod impact strength test (notched)	ISO 180:2019 (A1)	8.33 kJ/m2
Heat deflection temperature	ISO 180:2023 (method A)	74.2°C
Vicat softening temperature	ISO 306:2022	97.3°C

G

Group II – Dark ¹⁰



Nike Rise Westfield UK



The Evolve Chair by Tom Robinson UK



LUSH Glatt Switzerland



Adidas floor, by SAMJI Studio France




Morning co-working space France

Group II – Dark 11






PATTERN NO. 5 #PS1203 Refrigerators, consumer electronics, spools



BLACK LOLLIPOP #PS1602


plastic cutlery





Q.ÿ. SEA FOAM DARK #PS2401

Consumer electronics and single-use plastic cutlery



DARK KNIGHT Ô.ö. #PS1103 Spools and consumer electronics

*Panel colour may vary from the photo



Consumer electronics and single-use

REVERSE TIMELESS DUO 0.0 #PS1202 Refrigerators and spools, consumer electronics





GHOST Q.ộ. #PS1703 Refrigerators, TV's, keyboards, mice, spools



UV resistant -0-

Waterproof

Test name	ISO	Indicator
Tensile modulus	ISO 527-2:2012 (method A)	1825 MPa
Tensile strength	ISO 527-2:2012 (method A)	24.0 MPa
Modulus of elasticity	ISO 178:2010 (method B)	1889 N/mm²
Flexural strength	ISO 178:2010 (method B)	52.01 N/mm ²
Izod impact strength test (notched)	ISO 180:2019 (A1)	7.19 kJ/m2
Heat deflection temperature	ISO 180:2023 (method A)	74.2°C
Vicat softening temperature	ISO 306:2022	96.9°C

Group III – Terrazzo¹²



Bar for London Design Festival 2023 by Isola UK



Soho Boutique Turia Hotel Spain



Installation for Oslo Design Fair 2021 Norway



De Bijenkorf department store Netherlands



Furniture for Paris Design Week 2023 France

¹³ Group III – Terrazzo






SAPPHIRE TERRAZZO #PS1801 Spools

TERRAZZO NUOVO #PS1901 Refrigerators

 \Diamond



Scratch resistant

0 1

UV resistant

Test name	ISO	Indicator
Tensile modulus	ISO 527-2:2012 (method A)	1877 Mpa
Tensile strength	ISO 527-2:2012 (method A)	22.6 Mpa
Modulus of elasticity	ISO 178:2010 (method B)	1999 N/mm²
Flexural strength	ISO 178:2010 (method B)	51.77 N/mm ²
Izod impact strength test (notched)	ISO 180:2019(A1)	6.89 kJ/m2
Heat deflection temperature	ISO 180:2023 (method A)	74.5*C
Vicat softening temperature	ISO 306:2022	97.2 *C

▲ Group IV – Grey & Emerald¹⁴



McDonald's UK exterior cladding UK



Regina collection lamps, by Robin Italy



Furniture for London Design Festival, by Isola France



Reel, by Tobia Zambotti Iceland

¹⁵ Group IV – Grey & Emerald



MARBLE DESERT O description description of the second seco




GREYCIOUS O #PS1702 Home appliances and refrigerators



PURE GREY #PS1102 Home appliances

 \Diamond



EMERALD GHOST #PS1706 Home appliances

*Panel colour may vary from the photo

Ô.ö.



int -<mark>Ò</mark>-

UV resistant

Test name	ISO	Indicator
Tensile modulus	ISO 527-2:2012 (method A)	2025 MPa
Tensile strength	ISO 527-2:2012 (method A)	24.6 MPa
Modulus of elasticity	ISO 178:2010 (method B)	2101 N/mm ²
Flexural strength	ISO 178:2010 (method B)	55.39 N/mm ²
Izod impact strength test (notched)	ISO 180:2019 (A1)	7.92 kJ/m2
Heat deflection temperature	ISO 180:2023 (method A)	75.5°C
Vicat softening temperature	ISO 306:2022	96.3°C


Group V – Marbellous¹⁶



Marbellous chair by SAMJI



The Gabrielle table by SAMJI



Installation for Dutch Design Week

¹⁷ Group V – Marbellous **2**



*Panel colour may vary from the photo

Scratch resistant

UV resistant

Test name	ISO	Indicator
Tensile modulus	ISO 527-2:2012 (method A)	1954 MPa
Tensile strength	ISO 527-2:2012 (method A)	25.2 MPa
Modulus of elasticity	ISO 178:2010 (method B)	2000 N/mm ²
Flexural strength	ISO 178:2010 (method B)	50.11 N/mm ²
Izod impact strength test (notched)	ISO 180:2019 (A1)	9.92 kJ/m2
Heat deflection temperature	ISO 180:2023 (method A)	75.9°C
Vicat softening temperature	ISO 306:2022	97.5°C

Group VI – Translucent ¹⁸



Installation "Embracing the Elements" Ireland




Installation "An Iceberg in the Desert Dubai" UAE



Installation "Climate Stripes" by Isola France



WAVE Chair by Rouven Westerholt France



Library by PlaceTic France



London Design Festival UK

¹⁹ Group VI – Translucent **4**



 \Diamond

 \Diamond

 \Diamond

 \triangle

MALDIVES #PS1301 CD cases



CORAL REEF #PS1501 Industrial tubes, acoustic panels \Diamond

 \Diamond



TRANSLUCENT NEON GREEN () #PS1306 CD cases



TRANSLUCENT RED #PS1308 Industrial tubes



TRANSLUCENT GREEN #PS1303 Refrigerators



TRANSLUCENT PINK #PS1304 Refrigerators and CD cases



TRANSLUCENT BLACK () #PS1309 Refrigerators, spools, CNC shavings



ICE LOLLIPOP #PS1503 Tubes, single-use plastic cutlery



AQUA DRIFT #PS1508 CD cases, cutlery

TRANSLUCENT CLEARImage: Constraint of the second secon



YELLOW SUBMARINE #PS1707 Refrigerators, single-use plastic cutlery



TRANSLUCENT BURGUNDY #PS1310 CD cases




 \Diamond



 \Diamond

Group VI – Translucent²⁰



Test name	ISO	Indicator
Tensile modulus	ISO 527-2:2012 (method A)	3229 MPa
Tensile strength	ISO 527-2:2012 (method A)	49.2 MPa
Modulus of elasticity	ISO 178:2010 (method B)	3283 N/mm ²
Flexural strength	ISO 178:2010 (method B)	108.48 N/mm ²
Izod impact strength test (notched)	ISO 180:2019 (A1)	1.86 kJ/m² (C)
Heat deflection temperature	ISO 180:2023 (method A)	78.8°C
Vicat softening temperature	ISO 306:2022	96.3°C

²¹ Group VII – Salt Dune



Furniture for the Architizer A+ awards ceremony France




Reception for THBX store Netherlands



Spacesworks co-working centre Norway



Longevity Hub Prague Czechia



Paris Design Week 2023 France

Group VII – Salt Dune²²



SALT DUNE #PS1701 Spools

*Panel colour may vary from the photo

Scratch resistant

- UV resistant

Test name	ISO	Indicator
Tensile modulus	ISO 527-2:2012 (method A)	2602 MPa
Tensile strength	ISO 527-2:2012 (method A)	34.9 MPa
Modulus of elasticity	ISO 178:2010 (method B)	2690 N/mm ²
Flexural strength	ISO 178:2010 (method B)	74.87 N/mm ²
Izod impact strength test (notched)	ISO 180:2019 (A1)	9.10 kJ/m² (C)
Heat deflection temperature	ISO 180:2023 (method A)	79.0°C
Vicat softening temperature	ISO 306:2022	98.4°C



Polygood®

hello@thegoodplasticcompany.com https://polygood.com

Netherlands The Good Plastic Company B.V. +31 (0)20 399 1260 KVK 73403636 Keersluisweg 7, Hal 1, 1332 EE Almere, Netherlands



B